



# Cetol® Marine Natural Teak

Wood Treatment

Synthetic wood treatment with UV protection

## PRODUCT DESCRIPTION

Cetol® Marine Natural Teak is a flexible and breathable, satin translucent wood finish for use above the waterline on interior and exterior woods. It has a rich golden color that will enhance the natural beauty and grain of wood. It is formulated with the same ease of application and maintenance that all Cetol® products are known for but with Next Wave™ UV-absorbing technology.

## PRODUCT INFORMATION

<b>Colour</b>	IVA316-Cetol Marine Natural Teak
<b>Finish</b>	Satin
<b>Specific Gravity</b>	0.87
<b>Volume Solids</b>	28.0%
<b>Typical Shelf Life</b>	5 yrs
<b>VOC (As Supplied)</b>	490 g/ltr
<b>Unit Size</b>	1 US Quart 1 US Gallon

## DRYING/OVERCOATING INFORMATION

### Drying

73°F

Touch Dry [ISO]  
Hard Dry [ISO]

4hrs  
24hrs

### Overcoating Substrate Temperature

73°F

Overcoated By

Min	Max	Min	Max	Min	Max	Min	Max
-----	-----	-----	-----	-----	-----	-----	-----

Cetol®

24hrs -

## APPLICATION AND USE

### Preparation

**NEW EXTERIOR/INTERIOR WOOD:** Wipe the wood with Interlux® Special Thinner 216 to remove any natural surface oils and contaminants. Allow to dry, sand surfaces with 180-220 (grade) grit paper (always sand along the length of the grain). Remove all sanding residue by vacuuming the surface. Wipe the surface with Interlux Special Thinner 216 and allow to dry completely prior to application of Cetol® Marine Natural Teak.

### EXTERIOR/INTERIOR - PREVIOUSLY COATED WOOD :

**(non Cetol Marine Products):** Remove all coatings prior to application of Cetol® Marine Natural Teak. To remove old coating, either sand with 120-180 (grade) grit paper or use Interlux Interstrip 299E chemical stripper which has been designed for marine use. Once previous coating has been removed, follow instructions for New Exterior/Interior wood.

**EXTERIOR - WEATHERED WOOD OR PREVIOUSLY OILED WOOD:** To ensure good adhesion of Cetol® Marine Natural Teak on weathered or previously oiled wood, use Interlux Premium Teak Restorer with a nylon scruffing pad as per instructions on label. Rinse with fresh water and allow to dry. Once complete follow instructions for New Exterior/Interior wood.

### Method

The wood moisture content should be below 18%. Apply liberally using a long-haired bristle brush, smoothly, in the direction of the grain. Keep a wet edge to prevent lap marks and thoroughly saturate end grains where possible. Apply 3 coats of Cetol® Marine Natural Teak. Always allow 24 hours drying time in between coats. Sanding between coats is not

recommended as this will result in a reduction of dry film thickness. Recommended film thickness must be applied to ensure effective product performance.

Make regular inspections to all coated areas. Problem areas should be attended to immediately and maintenance coats should be routinely applied. If the coating is allowed to weather beyond the regular maintenance period of 1 year, returning this surface to excellent condition will be more difficult. Before application of a maintenance coat of Cetol® Marine Natural Teak, clean the surface with Interlux All Purpose Boat Soap to remove any surface contaminants as per instructions on label. If blue fungi or mildew are present then they can be treated with Interlux Premium Teak Restorer with a nylon scruffing pad as per instructions on label. Rinse with fresh water and allow to dry. Sand lightly with 220-320 (grade) grit paper. After sanding, wipe with Interlux® Special Thinner 216 and let to dry thoroughly prior to the application of the maintenance coat of Cetol® Marine Natural Teak.

If using as a deck paint, sprinkle Interlux Intergrip (non-skid compound) onto the wet surface of the second coat of Cetol® Marine Natural Teak. Allow to dry for 24 hours. Remove excess Intergrip using a vacuum. Maintenance requirements may be increased when Intergrip is used. If high gloss finish is required, use Cetol® Marine Gloss following the initial application of Cetol® Marine Natural Teak. Refer to Cetol® Marine Gloss datasheet for further details. Cetol® Marine Gloss is NOT suitable for use on decks.

#### Hints

**Mixing** Stir thoroughly before use.

**Thinning** Do not thin.

**Cleaner** Special Thinner 216.

**Ventilation and Humidity Control** Ensure adequate ventilation during use.

**Airless Spray** Not recommended.

**Roller** Not recommended.

**Other** Before applying any Cetol® products, prepare a 3 coat test sample on your wood to confirm desired color results. To achieve optimal color results always use the same Cetol® product initially applied when overcoating or applying maintenance coats.

#### Some Important Points

If Cetol® Marine Natural Teak is spilled on gelcoat, remove immediately. Difficult stains may be removed from gelcoat with Interlux Fiberglass Solvent Wash 202. Do not allow excess Fiberglass Solvent Wash 202 to remain on gelcoat. For painted surfaces ONLY use Interlux Special Thinner 216. Do not allow excess Special Thinner 216 to remain on painted surfaces. Do not apply at temperatures within 3°C of dew point or in wet weather. Substrate temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Ambient temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Product temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Avoid painting in direct sunlight.

#### Compatibility/Substrates

Suitable for use on all types of wood including oily timbers such as Teak.

#### Number of Coats

2-3 as per specification.

#### Coverage

(Theoretical) - 305.3 (ft<sup>2</sup>/Gal) - up to 400 ft<sup>2</sup>/gal (10 m<sup>2</sup>/lt) per coat. On new wood the coverage of the first coat will be lower as Cetol® Marine Natural Teak will penetrate the wood.

(Practical) - Dependant upon the surface roughness and conditions of application.

#### Recommended DFT

#### Application Methods

Brush

### TRANSPORTATION, STORAGE AND SAFETY INFORMATION

#### Storage

##### GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Cetol® to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

##### TRANSPORTATION:

Cetol® should be kept in securely closed containers during transport and storage.

#### Safety

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Cetol® cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

## IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.



Sikkens<sup>®</sup>, the Akzo Nobel logo and other products mentioned in this publication are trademarks of, or licensed to Akzo Nobel.

## Regional Addresses

### Head Office

International Paint Ltd  
P O Box 20980  
Oriel House  
16 Connaught Place  
London W2 2ZB  
United Kingdom  
tel: +44 (0) 171 479 6000  
fax: +44 (0) 171 479 6500

### European Region

International Paint Ltd  
Stonegate Lane  
Felling, Gateshead  
Tyne & Wear NE10 0JY  
United Kingdom  
tel: +44 (0) 191 469 6111  
fax: +44 (0) 191 438 3977

### Asia Region

International Paint Singapore  
(Pte) Ltd  
449 Tagore Industrial Avenue  
01-03 Hong Joo Industrial  
Building  
Singapore 787820  
tel: +65 6453 1981  
fax: +65 6453 1778

### Australasia Region

International Paint  
115 Hyde Road  
Yeronga, Brisbane  
Queensland 4104  
Australia  
tel: +61 (0) 7 3892 8866  
fax: +61 (0) 7 3892 4287

### North America Region

International Paint LLC  
2270 Morris Avenue  
Union  
New Jersey 07083  
USA  
tel: +1 (0) 908 686 1300  
fax: +1 (0) 908 686 8545

### South America Region

International Paint  
Rod Rap tavares, KM 18.5  
Predio Administrativo 11  
Butanta CEP 05577-300  
Sao Paulo, Brazil  
tel: +55 (0) 11 3789 2000  
fax: +55 (0) 11 3789 2200



Ref: 00003872  
Issue Date: 29-Oct-2007  
Supersedes: 3-Oct-2007