

# Cruiser UNO

## Antifouling

One Coat, One Season, One Choice



### PRODUCT DESCRIPTION

One coat antifouling designed for both power (up to 25 knots) and sailing boats.

\* Single season's antifouling protection

\* In most cases there is no need to seal main stream antifouling schemes

\* No need to sand before re-coating

### PRODUCT INFORMATION

Colour	YBA203-Shell White, YBA210-Blue, YBA234-Navy, YBA255-Red , YBA295-Black
Finish	Matt
Specific Gravity	1.6
Volume Solids	49% average
Typical Shelf Life	2 yrs
VOC (As Supplied)	443 g/lt
Unit Size	750 ml 2.5 Lt

### DRYING/OVERCOATING INFORMATION

	Drying			
	5°C (41°F)	15°C (59°F)	23°C (73°F)	35°C (95°F)
Touch Dry	1 hrs	45 mins	30 mins	20 mins
Immersion	7 hrs	5 hrs	2 hrs	2 hrs

Note: Max. Immersion Times are as follows: 5-15°C - 3 mths; 23°C - 2 mths; 35°C - 1 mth

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Min	Max	Min	Max	Min	Max	Min	Max	
Cruiser UNO	16 hrs	ext	10 hrs	ext	6 hrs	ext	4 hrs	ext

### APPLICATION AND USE

<b>Preparation</b>	<p><b>PREVIOUSLY ANTIFOULED SURFACE</b></p> <p><b>In Good Condition</b> Rinse with fresh water and allow to dry. If old antifouling is incompatible or unknown, seal with Primocon.</p> <p><b>In Poor Condition</b> Use Interstrip to remove all traces of antifouling.</p> <p><b>PRIMING</b> All preparation for bare substrates is covered on the appropriate primer datasheet.</p> <p><b>BARE GRP</b> Gelshield 200 for osmosis protection, or Primocon.</p> <p><b>STEEL/IRON</b> Interprotect or Primocon.</p> <p><b>LEAD</b> Etch Primer followed by Interprotect or Primocon.</p> <p><b>WOOD</b> Preserve, if required, with Intertox. Prime with Interprotect or Primocon.</p>
<b>Method</b>	<p>Apply 1 coat only. 2 coats will be required in the first season if applying to a new hull, one that has been stripped back to bare substrate, or over antifouling in poor condition. 2 coats are recommended for leading and trailing edges, waterline, rudder and keel.</p>
<b>Hints</b>	<p><b>Mixing</b> Stir well before use.</p> <p><b>Thinner</b> YTA085 Thinners No.3</p> <p><b>Thinning</b> Thinning is not recommended.</p> <p><b>Cleaner</b> YTA085 Thinners No.3</p> <p><b>Ventilation and Humidity Control</b> Ensure adequate ventilation during use.</p> <p><b>Airless Spray</b> Pressure: 176-210 bar. Tip Size: 2180.</p> <p><b>Other</b> For Airmix spray application: Pressure: 2.5 bar. Tip Size: 20-113. True colour will develop after immersion. Take care to apply all the paint calculated even if it means applying an extra coat. It is important for performance to apply the correct thickness.</p>
<b>Some Important Points</b>	<p>To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide. Product temperature should be minimum -5°C and maximum 35°C. Ambient temperature should be minimum -5°C and maximum 35°C. Substrate temperature should be minimum 1°C above dew point and maximum 35°C.</p>
<b>Compatibility/Substrates</b>	<p>GRP, Wood, Steel/Iron, Lead. Not suitable for use over Aluminium/Alloy substrates or zinc sprayed surfaces. Can be</p>

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

# Cruiser UNO

## Antifouling

One Coat, One Season, One Choice



applied direct over most types of antifouling, provided they are in sound condition Not compatible with VC 17m systems. Please contact your local International Coatings Ltd. representative for further information.

<b>Number of Coats</b>	1-2 coats as specified
<b>Coverage</b>	(Practical) - 8.5 m <sup>2</sup> /lt by brush; 3.0 m <sup>2</sup> /lt by spray.
<b>Recommended DFT per coat</b>	52 microns dry by brush
<b>Recommended WFT per coat</b>	106 microns wet by brush
<b>Application Methods</b>	Airless Spray, Brush, Airmix, Roller

### TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<p><b>GENERAL INFORMATION:</b></p> <p>Exposure to air and extremes of temperature should be avoided. For the full shelf life of Cruiser UNO to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.</p> <p><b>TRANSPORTATION:</b></p> <p>Cruiser UNO should be kept in securely closed containers during transport and storage.</p>
<b>Safety</b>	<p><b>GENERAL:</b> Contains biocides. Antifouling should only be wet sanded. Never dry sand or burn-off old antifouling. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p><b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of Cruiser UNO cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>
<b>IMPORTANT NOTES</b>	<p><i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i></p>

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.