

PRODUCT DESCRIPTION

A two-component, fast drying, high gloss finishing aliphatic acrylic polyurethane. Shows excellent colour and gloss retention, durability, resistance to weathering and salt water. Specified for the protection and finishing of non-immersed surfaces of steel, non-ferrous metals, timber and fiberglass. Developed specifically for the marine market where high visual and aesthetic standard is a prerequisite for excellence. It can be used on internal and external areas, providing good flexibility and provides protection against spills and stains of various chemicals.

PRODUCT INFORMATION

Colour	YNA102-High Gloss base (available in a wide range of colours), YLA101-Semi Gloss base (available in a wide range of colours), YNA101-White (Semi Gloss), YNB000*-White (High Gloss)
Finish	Gloss
Specific Gravity	L-Code (Awlcraft SE Solid Basecoat)
Volume Solids	42%
Mix Ratio	4:1 by volume
Converter/Curing Agent	YGA001
Typical Shelf Life	12 mths
VOC (As Supplied)	576 g/lit
Unit Size	0.9 lit, 3.6 lit

DRYING/OVERCOATING INFORMATION

	Drying							
	10°C (50°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	40 mins		30 mins		20 mins		15 mins	
Pot Life	5 hrs		5 hrs		5 hrs		5 hrs	

	Overcoating							
	Substrate Temperature							
	10°C (50°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Perfection	8 hrs	ext	7 hrs	ext	6 hrs	ext	4 hrs	ext

Note: A glossy surface can prevent the adhesion of further coats. Such a surface must be sanded lightly.

APPLICATION AND USE

Preparation	<p>ALUMINIUM, FIBERGLASS & GALVANISED METAL</p> <p>Wash with fresh water and degreasers to remove any dirt, grease and other surface contaminants, then sand. All surfaces to be coated must be clean, dry and free from contaminants. Apply one x 15 micron DFT coat of Galverette. Wait for 6 hours, then apply two x 125 micron DFT coats of Intergard Yacht at further 6 hour intervals, as per the instructions specified on the label. After 6 hours, apply 2 -3 coats of Perfection, as per the instructions specified on the label.</p> <p>WOOD</p> <p>Wash with fresh water and degreasers to remove any dirt, grease and other surface contaminants, then sand. All surfaces to be coated must be clean, dry and free from contaminants. Wait for 6 hours, then apply two x 125 micron DFT coats of Intergard Yacht at further 6 hour intervals, as per the instructions specified on the label. After 6 hours, apply 2 -3 coats of Perfection, as per the instructions specified on the label.</p> <p>STEEL</p> <p>Wash with fresh water and degreasers to remove any dirt, grease and other surface contaminants. All surfaces to be coated must be clean, dry and free from contaminants. Apply one x 15 micron DFT coat of Galverette. Wait for 6 hours, then apply two x 125 micron DFT coats of Intergard Yacht at further 6 hour intervals, as per the instructions specified on the label. After 6 hours, apply 2 -3 coats of Perfection, as per the instructions specified on the label.</p>
Hints	<p>Thinner GTA713 may be used if necessary</p> <p>Cleaner GTA713</p> <p>Ventilation and Humidity Control Apply in dry, well ventilated conditions. Do not apply this product if humidity</p>

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2015.

Some Important Points	exceeds 85%. Induction Time after Mixing = 15 Minutes. Not suitable for permanently immersed surfaces.
Coverage	(Theoretical) - 12 m ² /lt
Recommended DFT per coat	35 microns dry
Recommended WFT per coat	83 microns wet
Application Methods	Conventional Spray Application by brush/roller is recommended for small areas only.

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Perfection to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight. TRANSPORTATION: Perfection should be kept in securely closed containers during transport and storage.
Safety	GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of Perfection cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.
IMPORTANT NOTES	<i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i>

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2015.