

Trilux Propeller

Antifouling

For Propellers, Outboards and Sterngear



PRODUCT DESCRIPTION

Trilux Propeller is a hard antifouling that is specially formulated for use on outdrives, outboard legs, propellers and sterngear.

- * Aerosol spray is ideal for painting awkward shapes and difficult to reach areas.
- * Quick and easy application saves you time and effort.
- * Suitable for use on aluminium and stainless steel.

PRODUCT INFORMATION

Colour	YBC000-Black , YBC001-Grey
Finish	Matt
Specific Gravity	0.8
Volume Solids	9% average
Typical Shelf Life	2 yrs
VOC (As Supplied)	691 g/lt
Unit Size	500 ml

DRYING/OVERCOATING INFORMATION

	Drying							
	0°C (32°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Immersion	3 hrs		3 hrs		3 hrs		3 hrs	
	Overcoating							
	Substrate Temperature							
Overcoated By	0°C (32°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Trilux Propeller	30 mins	ext	30 mins	ext	30 mins	ext	30 mins	ext

APPLICATION AND USE

Preparation	Prime bare metal and factory enamelled surfaces with 2 coats of VC Prop-O-Drev Primer. This is essential on aluminium and alloy as Trilux Propeller is NOT suitable for direct application. For best results on previously antifouled surfaces, remove existing paintwork. Alternatively, abrade with wet 240 grade paper.
Method	Spray sparingly 10-15 cm (4-10") from the surface. Apply a minimum of 3 coats, allowing 30 mins between coats.
Hints	<p>Mixing Shake can vigorously. Once mixing ball is heard, shake for minimum 2 minutes prior to use. After spraying, invert can and spray for 2 seconds to clean the nozzle.</p> <p>Thinner VC General Thinner.</p> <p>Cleaner VC General Thinner.</p> <p>Other Take care to apply all the paint calculated even if it means applying an extra coat. It is important for performance to apply the correct thickness.</p>
Some Important Points	To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide. Product temperature should be minimum 0°C and maximum 35°C. Ambient temperature should be minimum 0°C/32°F and maximum 35°C/95°F. Substrate temperature should be minimum 1°C above dew point and maximum 35°C.
Compatibility/Substrates	Suitable for use on all substrates including suitably primed Aluminium/Alloy and Zinc-sprayed metals. Also suitable for factory enamelled finishes.
Number of Coats	3 minimum
Coverage	Approx. 1 can per medium-sized outdrive.

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>GENERAL INFORMATION:</p> <p>Exposure to air and extremes of temperature should be avoided. For the full shelf life of Trilux Propeller to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.</p> <p>TRANSPORTATION:</p> <p>Trilux Propeller should be kept in securely closed containers during transport and storage.</p>
Safety	GENERAL: Contains biocides. Antifouling should only be wet sanded. Never dry sand or burn-off old antifouling. Read

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

Trilux Propeller

Antifouling

For Propellers, Outboards and Sterngear



the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Trilux Propeller cannot be disposed of through the municipal waste route or dumped without permit.

Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.