

VC Prop-O-Drev Primer

Primers

Protection for Drives and Propellers



PRODUCT DESCRIPTION

VC Prop-O-Drev Primer is specially formulated for use with Prop-O-Drev on outdrives, outboard legs, propellers and sterngear.

* Aerosol ideal for painting awkward shapes

It offers excellent adhesion to properly prepared metal and factory enamelled surfaces.

PRODUCT INFORMATION

Colour	YPA688-Grey
Finish	Matt
Specific Gravity	0.8
Volume Solids	9%
Typical Shelf Life	2 yrs
VOC (As Supplied)	691 g/lit
Unit Size	300 ml

DRYING/OVERCOATING INFORMATION

	Drying					
	5°C (41°F)		15°C (59°F)		23°C (73°F)	
Touch Dry	2 hrs		1 hrs		30 mins	
	Overcoating					
	Substrate Temperature					
Overcoated By	5°C (41°F)		15°C (59°F)		23°C (73°F)	
	Min	Max	Min	Max	Min	Max
Trilux Prop-O-Drev	3 hrs	6 mths	2 hrs	6 mths	1 hrs	6 mths
VC Prop-O-Drev Eco	3 hrs	6 mths	2 hrs	6 mths	1 hrs	6 mths
VC Prop-O-Drev Primer	3 hrs	6 mths	2 hrs	6 mths	1 hrs	6 mths

Note: If maximum overcoating time is exceeded, sand the surface with dry 240 grade wet and dry paper.

APPLICATION AND USE

Preparation	Shield nearby areas and clean surface with VC General Thinner. Sand with 120 grade wet and dry paper, used dry, wiping clean with VC General Thinner.
Method	Spray 10-25 cm (4-10") from the surface. Apply second coat following overcoating times specified.
Hints	Mixing Shake can thoroughly. Cleaner YTA600 VC General Thinner.
Some Important Points	Product temperature should be minimum 0°C and maximum 35°C. Ambient temperature should be minimum 0°C/32°F and maximum 35°C/95°F. Substrate temperature should be minimum 1°C above dew point and maximum 35°C.
Compatibility/Substrates	For use on Aluminium/Alloy, Zinc-sprayed Surfaces and Lead. Also suitable for factory enamelled finishes.
Number of Coats	2
Coverage	(Theoretical) - 3.33 m ² /lit 1 m ² /300 ml can.
Application Methods	Aerosol can

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of VC Prop-O-Drev Primer to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight. TRANSPORTATION: VC Prop-O-Drev Primer should be kept in securely closed containers during transport and storage.
Safety	GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

VC Prop-O-Drev Primer

Primers

Protection for Drives and Propellers



Remainders of VC Prop-O-Drev Primer cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.