

Handy Specification

VARNISH SCHEME RECOMMENDATIONS

STAGE	PRODUCT	PREVIOUSLY VARNISHED	BARE WOOD	OILY WOOD (TEAK, IROKO)		WORK TIME*	OVERCOATING TIME**
				PREVIOUSLY VARNISHED	BARE WOOD		
ABRADE		280-320 grade	80-180, then 280 grade	280-320 grade	80-180, then 280 grade	1	
PRE-TREATMENT	UCP or Schooner®, Goldspar®, Original, Perfection®	∅	1 Thinned 10 - 15%	∅	1 **** Thinned 10 - 15%	1	14
VARNISH CHOICE Follow one complete product scheme	Schooner®	4 ***	4-6 ***	4 ***	4-6 ***	1	14
	Goldspar®	3	3	3	∅	1	15
	Goldspar® Satin	3	3	3	∅	1	15
	Original	3	3	3	∅	1	24
	Perfection®	4	4	4 †	4	1	14
TOTAL PROJECT TIME:						3 WEEKENDS	

* Average time to apply one coat to average sized boat of 8m/25 feet.

** Minimum wait time between coats or between overcoating with the next step in the system, at a temperature of 15°C.

Please consult product data sheets (available from International.yachtpaint.com) for overcoating times at different temperatures. Data sheets may also be viewed via our website yachtpaint.com.

*** For increased durability and added depth of gloss, apply additional coats of Schooner®.

****Do not use UCP, Goldspar, Original.

† Always avoid applying a two-part product onto a surface previously varnished with a one-part varnish.

KEY:  No. of coats  Minutes  Hours  Do not use for this purpose

CARING
FOR
YOUR WOOD