

# Handy Specifications

## CONVENTIONAL ONE-PART PRODUCTS

This system provides a good level of protection

STAGE	PRODUCT	ALUMINUM	STEEL	WOOD
CLEAN	Fiberglass Solvent Wash 202 or Fiberglass Surface Prep YMA601 or Special Thinner 216	YES	YES	202 or 216
SAND		grind or sandblast	grind or sandblast	Sand with 80 grit sandpaper
SURFACE PRIMER	Viny-Lux Primewash 353/354	1	1	Ø
PRIMER	Primocon	1	1	1 (thinned 10-15%)
FILLER	Watertite	as needed	as needed	as needed
PRIMER	Primocon	2-3	2-3	1-2
ANTIFOULING	Interlux® Antifouling	2-3	2-3	2-3

## HIGH PERFORMANCE TWO-PART PRODUCTS

This system provides the maximum level of antifouling

STAGE	PRODUCT	ALUMINUM	STEEL	WOOD
CLEAN	Fiberglass Solvent Wash 202 or Fiberglass Surface Prep YMA601 or Special Thinner 216	YES	YES	202 or 216
SAND		grind or sandblast	grind or sandblast	Sand with 80 grit sandpaper
SURFACE PRIMER	Viny-Lux Primewash 353/354	1	1	Ø
PRIMER	InterProtect® 2000E	1	1	1
FILLER	Watertite	as needed	as needed	as needed
PRIMER	InterProtect® 2000E	2-3	2-3	1-2
ANTIFOULING	Interlux® Antifouling	2-3	2-3	2-3

Please consult product data sheets (available at [yachtpaint.com](http://yachtpaint.com)) for overcoating times at different temperatures.

ANTIFOULING

## VC®17M & VC®17M EXTRA

This system provides the maximum level of antifouling and blister protection

STAGE	PRODUCT	FIBERGLASS	WOOD	STEEL
CLEAN	Fiberglass Solvent Wash 202 or Fiberglass Surface Prep YMA601 or Special Thinner 216	YES	202 or 216	202 or 216
SAND		80 grit sandpaper	Sand with 80 grit sandpaper	grind or sandblast
SURFACE PRIMER	Viny-Lux Primewash 353/354	Ø	Ø	1
FILLER	Watertite	as needed	as needed	as needed**
PRIMER	VC® Tar2	4-5	4-5	4-5
ANTIFOULING	VC®17m & VC®17m Extra	2-3	2-3	2-3

If gelcoat blister protection is not needed the antifouling paint can be applied directly to bare fiberglass.

\*\*If fairing is necessary on underwater metal surfaces apply 1 coat of InterProtect® 2000E/2001E after blasting or sanding, wait 4 hours and apply Interfill® or Watertite Epoxy Fairing Compound, then apply 4-5 coat of VC Tar2.

KEY:  No. of coats

 Do not use for this purpose