

PRODUCT	BRUSH	SPRAY	CLEANUP	% THINNER REQUIRED	
				BRUSH	SPRAY
Perfection® Polyurethane/Epoxy Primerkote	2333N	2316N	2333N or 2316N	As needed 5-10%	As required 25-35% max.
Toplac Silicone Copolymer	333	216	216	As required 10% max.	10-15%
Brightside®	333	216	216	As required 10% max.	10-15%
Yacht Enamel	333	216	216	As required 10% max.	10-15%
Interstain	333	N/A	333	As required	N/A
Varnishes	333	216	216	As required 10% max.	5-10%
Bottom Paints (conventional)	216	216	216	10% 1st coat wood only	As required 10% max.
Micron® Extra, Micron® CSC, TriLux® 33®, TriLux®, Tri-LUX® II, Ultra	433	216	433 or 216	As required 10% max.	As required 20-30% max.
Fiberglass Bottomkote® ACT	216	216	216	10% 1st coat wood only	As required 10% max.
Fiberglass Bottomkote® Aqua	6216	6216	Water	As required 10% max.	As required 10% max.
VC® Offshore	355	355	355	10% 1st coat wood only	As required 10% max.
VC®17m Extra, VC®17m	V172	V172	V172	10-15% max.	10-15% max.
Interprotect 2000E & 3000	2333N	2316N	2333N/2316N	5-10%	10-15%
VC Performance Epoxy	2333N	2316N	2333N/2316N	5-10%	10% Maximum

These are only general requirements. Thinner quality and type vary depending upon temperature and specific application.
 N/A – Not applicable
 Spraying of anti fouling paints is not permitted in Canada.



IMPORTANT: TO FIND MORE INFORMATION ON HEALTH AND SAFETY INCLUDING MATERIAL SAFETY DATA SHEETS, VISIT OUR WEBSITE yachtpaint.com



EVERYTHING
ELSE